


# SlopeGrid

## Cell Detail

	<p><b>Manufactured Cell Depths</b></p> <p>4"      100 mm 6"      150 mm</p> <p>Weld Distance:    17" (432 mm ± 2.5 mm)</p> <p><b>Expanded Unit Dimensions</b> 8' x 29' (2.4 m x 8.7 m)</p>
---	--

## Material Specifications

Properties	Test Method	Test Value
Material Composition	ASTM D1505	Polymer; virgin HDPE Density: 0.9574 g/cm <sup>3</sup>
Nominal Sheet Thickness	ASTM D5199	1.45 mm
Environmental Stress Cracking	ASTM D1693	>4500 Hrs.
Stabilizer	ASTM D297-13	1.55% carbon black
Short Term Seam Peel Strength	4" (100 mm) 6" (150 mm)	1542 N 2170 N
Long Term Seam Peel Strength	A 100 mm (4inch) wide section sample shall support a (160 lb.) load for a period of 7 days (168 hrs.) minimum in a temperature controlled environment undergoing a temperature change on a 1 hour cycle from ambient room temperature to (130° F)	

## Product Description

Item Code	Cell Depth	Expanded Unit Dimensions	Area / Unit	Pallet Qty
SLP-4	4" (100 mm)	8' x 29' (2.4 m x 8.7 m)	232 SF	18
SLP-6	6" (150 mm)	8' x 29' (2.4 m x 8.7 m)	232 SF	12

Cell-Tek Geosynthetics assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Cell-Tek Geosynthetics disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.